




Suzhou Bee-Tech CO., Ltd
Peel Strength Test Report

Operator: Mrs. Zhao

Test Date: 2022-3-2

File Name: ncover Sealing on PS Carrier Tape

Test Time: 9:10:36



Test Result: **Pass!**

	Min.	Max.	Range	Avg.	Variance	Std Dev.	Sqrt	CPK
Measurement								
Value:	20.8	23.8	3.0	22.1	0.96	0.9	22.2	4.5
Limit Value:	10.0	25.0						

Taping Machine: #1

Test Conditions: 60 °C, ± 60% RH

Carrier Tape

Name:
Lot No.:
Model:
Width: 88mm
Pitch: 52mm

Taping Condition

Sealing Mode: Step by step
Platform Temp: 25°C
Oven Temp: 40°C
Air Pressure: 0.385kg
Taping Speed: 25

Cover Tape

Name: ncover a
Lot No.:
Model: ncover a

Test Settings

Sealing Speed: 50
Peel Angle: 160-180°
Test Length: 300mm

Approval: Joe

Inspector: Zhao Jing